Patent Abstracts of Japan

99P3096

53

PUBLICATION NUMBER : 07268605
PUBLICATION DATE : 17-10-95

APPLICATION DATE : 29-03-94
APPLICATION NUMBER : 06058625

APPLICANT : NISSHIN STEEL CO LTD;

INVENTOR : SAITO MINORU;

INT.CL. : C23C 14/06 C23C 14/56 C23C 14/58 C23C 28/02

TITLE : PRODUCTION OF ALLOYED ZN-MG VAPOR DEPOSITION-COATED STEEL SHEET

ABSTRACT : PURPOSE: To obtain an alloyed Zn-Mg vapor deposition-coated steel sheet with Fe diffused to the surface of a plating layer and excellent in workability and corrosion resistance.

CONSTITUTION: A continuously traveled steel strip with the surface cleaned is introduced into a vacuum chamber, in a reducing or inert atmosphere, deposited with Mg at ≥100°C and then with Zn. An alloying heat treatment is applied to the strip immediately after leaving the vacuum chamber at 330-600°C for ≤10sec in an inert atmosphere or in the atmosphere so that the Fe is diffused from the substrate steel to the plating layer surface. The Zn-plated strip is held at 200-400°C for 1-25hr by using a heating furnace independent of the vacuum chamber to apply alloying heat treatment. Otherwise, the strip before Mg vapor deposition is kept at ≥100°C, the temp. is controlled so that the Zn-deposited strip is kept at 330-500°C, and alloying heat treatment is conducted by the sensible heat of the strip.